


Trinity Concrete Analysis – refinement of a possible safe level of pyrrhotite



- 527 houses analyzed
- no map cracking found with magnetic susceptibility loss below $5 \times 10^{-8} \text{ m}^3/\text{kg}$
- corresponds to approx. 0.15% pyrrhotite by weight
- in-line with recently adopted standards for aggregate